

Saturated, carboxylated polyester resin

General Description

PRIMID cure resin, 95/5 type, for industrial purposes cure with 180C X 10 min

- Outdoor durable
- Fast cure.
- Flow
- Flexibility

Starting Formulation

Component	Weight
P 8660	95.0
LC-552	5.0
Titanium dioxide ²⁾	50.0
LC-88 Flow agent ³⁾	1.5
Benzoin	0.5

Product Specifications

Property	Range	Test Method
Appearance	clear granule	Visual
Viscosity	30~40 pa.s	Longcai method
Acid value	30~35 mg KOH/g	Longcai method
Color	Max 10	Longcai method
Tg	appr. 60	Longcai method

Extrusion & Application Conditions

Extruder: Lingyu SLJ-20
Zone I temp.: 85~105℃
Zone II temp.: 90~110℃
Screw speed: 400~500rpm
Panel: 0.5mm pre-treated cold-rolled steel
Spray gun: Lingyu JP-80
Voltage: 60~90kV
Curing cycles: 10 min. @ 180℃

Packaging

- White PE bag, N.W.25kg/bag, 1000kg/pallet.

Storage

The product can be stably stored for at least one year when kept in closed containers in a dry place at temperature below 30℃. Avoid exposure to direct sunlight.

Film Properties

Item	Result	Test Method
Film thickness, μm	approx. 60	ASTM D1186
Gloss @ 60°, %	90 unit	ASTM D523
Direct/reverse impact, inch lbs	120/120	ASTM D2794
1/8" Conical mandrel	pass	ASTM D522
Adhesion(cross cut)	5B	ASTM D3359
Pencil hardness (Mar)	H	ISO 15184-98

Yantai Longcai Advanced Materials Co., Ltd

No.18 Hangzhou Road., Haiyang Development Zone, Yantai, China

Tel.: +86 535-330 6639

Fax: +86 535-330 6828

Post code: 265100

Web-site: www.longcester.com

E-mail: info@longcester.com

Disclaimer: The information given in this sheet is based on our present research and is believed reliable, but it is solely the user's responsibility to confirm by testing for its specific use.
LONGCAI MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.